

# DARASET<sup>®</sup> 580C

Non-Corrosive, Non-Chloride Set Accelerating Admixture

## Product Description

DARASET<sup>®</sup>580C is a non-corrosive, non-chloride admixture for concrete. It accelerates cement hydration, resulting in shortened setting times and increased early compressive strengths. DARASET 580C does not contain calcium chloride and is completely non-corrosive to reinforcing steel, metal decks, and to all metal components of admixture storage and dispensing systems. It meets the requirements of BS EN 934-2 and to Type C of ASTM

### Typical Properties

Appearance:	Clear Pale Brown Liquid
Specific Gravity:	1.34
Air Entrainment	Nil
Chloride Content:	Nil as per BS EN 480-10 C 494.

## Compatibility with Cements

In concrete mixtures, DARASET 580C accelerates the chemical reaction between Portland Cement and water. It speeds up the formation of gel – the binder that bonds concrete aggregates together. Accelerated gel formation, shortens the setting time

## Avantages

- Specially formulated to reduce concrete setting times and increase early strength of concrete in very cold conditions.
- May be used to reduce the time for which the concrete must be protected against freezing in ambient temperatures as low as -70C.
- May be used to speed finishing operations and/ or form removal, leading to savings in concrete construction costs.
- Provides set acceleration and early strength development similar to that provided by calcium chloride, but without the potential corrosive effects.
- Can be used where potential corrosion of embedded or stressed steel must be avoided.
- Can be used in concrete that is to be placed on steel clad or zinc coated steel decks where corrosion must be avoided.

of concrete, compensates for the set-slowing effects of cold weather and contributes to the development of higher strength. Gel formation promotes heat generation within the mixture, helping to protect the concrete from freezing during the critical first hour after placement.

In common with most concrete accelerators, the inclusion of DARASET 580C may reduce the ultimate compressive strength of concrete. The extent of strength loss should be established by conducting concrete trial mixes.

## Compatibility with other Admixtures

DARASET 580C is compatible with air-entraining admixtures such as the DAREX®AE Series; water reducers such as WRDA®P4 and WRDA P7; mid-range water reducers such as WRDA 90, and high-range water reducers such as DARACEM®205. DARASET 580C should not be premixed under any circumstances with other admixtures. While some admixtures can be usefully combined within the same mix, the performance of this product may well be affected by the presence of other chemicals. We recommend that GCP Applied Technologies be contacted for advice in all such circumstances.

## Addition Rates

**Range: 500 ml – 4000 ml per 100 kg cement (0.5%–4.0% volume by weight of cement)**

The amount of DARASET 580C used will depend on specific job conditions, on local materials and on the degree of set acceleration and early strength development required. Typical addition levels range from 500 ml to 2000 ml/100 kg cement, but levels as high as 4000 ml/100 kg cement can be used.

DARASET 580C is supplied ready for use. Since DARASET 580C may be used at high dosages, the concrete producer should account for the water contained in the DARASET 580C. One litre of DARASET 580C weighs approximately 1.40 kg.

DARASET 580C is supplied ready for use. Since DARASET 580C may be used at high dosages, the concrete producer should account for the water contained in the DARASET 580C.

One litre of DARASET 580C weighs approximately 1.40 kg and added to a concrete mixture will contribute 0.77 kg of water to that mixture.

Overdosing of DARASET 580C will produce an increased rate of setting and a reduction of the ultimate concrete strength.

## Dispensing

A range of equipment, advise on supply and fitting are available from GCP on request. DARASET 580C may be introduced on the sand, in the water, or at the end of the batch of cycles. Similar to all concrete admixtures, DARASET 580C should not come in contact with other admixtures prior to entering the concrete.

## Health and Safety

For further information see the DARASET 580C SDS (Safety Data Sheet) or consult GCP.

## Packaging

DARASET 580C is supplied in 210 litre free, non-returnable containers.

Alternatively, 1000 litre IBCs or bulk deliveries are also available

## Storage

DARASET 580C should be stored in original containers or suitable closed tanks, preferably out of direct sunlight and protected from extremes of temperature.

### Storage Life in Manufacturer's Drums:

12 months from date of manufacture

### Storage Life in Bulk Storage:

12 months from date of delivery

## Technical Service

The Technical Service Department of GCP Applied Technologies is available to assist you in the correct and best use of our products. These resources and advice are at your disposal entirely without obligation. Please contact:

GCP Applied Technologies  
Emirates Chemicals LLC  
Festival Tower, Suite 1701  
Dubai Festival City  
P.O. Box 5006  
Dubai, United Arab Emirates  
Email: [meinfo@gcpat.com](mailto:meinfo@gcpat.com)

[gcpat.uk](http://gcpat.uk) | United Kingdom customer service: +44 (0) 1480 478421

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

DARASET is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2016 GCP Applied Technologies Inc. All rights reserved.

GCP0082-1216 DARASET 580C-UAE

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP Applied Technologies (UK) Ltd, 487-488 Ipswich Road, Slough, SL1 4EP

This document is only current as of the last updated date stated below and is valid only for use in the United Kingdom. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on [www.gcpat.uk](http://www.gcpat.uk). Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2022-11-24

[gcpat.uk/solutions/products/daraset-580c-0](http://gcpat.uk/solutions/products/daraset-580c-0)