

MORTAIR[®] D

Mortar Air Entraining Agent

Product Description

MORTAIR[®]D is a liquid air-entraining agent for use in the production of air entrained mortar. It is normally used in conjunction with MORTARD[®]79/5 Mortar Retarder (see separate data sheet).

MORTAIR[®]D is formulated to allow ease of production of ready-to-use mortars complying with EN 998. MORTAIR[®]D yields a constant air content over a wide range of dosages. MORTAIR[®]D gives an extremely stable air system and complies with EN 934-3.

Advantages

- MORTAIR[®] D produces a stable air system with minimum air loss throughout the life of the plastic mortar
- Production of ready-to-use mortars complying with EN 998 is made easier because of the plateauing of air content and constant air content over a wide range of dosage
- Due to its dosage tolerance, the levels of entrained air when using MORTAIR[®] D are less susceptible to variation in fine aggregate grading and silt content of the fine aggregate
- Mortar containing MORTAIR[®] D has very good site acceptance because of its constant air content, reduced bleeding and predictable workability and life

Typical Properties

MORTAIR [®] D	
Appearance	Dark brown liquid
Specific Gravity (20 °C)	1.026
Alkali Content (eq.Na ₂ O)	0.50%
Chloride Content	Nil
Air Entrainment	See "Addition Rates"
Freezing Point	0 °C

Method Of Use

MORTAIR[®]D is supplied ready for use.

It should be added to the mortar mixes during the mixing process at the same time as the water or fine aggregate, but not directly onto cement. With good plant control, very consistent results can be obtained.

The amount of MORTAIR®D required is dependent on the characteristics of the mortar constituents and the level of air entrainment required. Factors which affect this are:

- Type and efficiency of the mixing equipment
- Water content
- Fine aggregate content, grading and type
- Cement/lime content and type
- Temperature

Compatibility

With Cements :

MORTAIR®D can be used with most types of Portland cements. It is also effective in mortar containing fly ash or ground granulated blastfurnace slag. For use with special cements we recommend contacting GCP Applied Technologies.

With Other Admixtures:

MORTAIR®D should not be premixed with other admixtures. The performance of the product will be affected by the presence of other chemical admixtures. We recommend that all admixtures be added separately into the mix.

Addition Rates

Range	100 ml - 500 ml per 100 kg cement
	0.10% - 0.50% (v/w) by wt. of cement
As a guide to trials an addition rate of 0.18 - 0.30% volume by weight of cement is suggested.	
For advice and assistance with trials we recommend that you consult GCP Applied Technologies.	

It is essential that preliminary plant trials are performed so that the actual dosage rates can be determined, taking into account the contributing factors stated (where MORTAIR®D is used in mortar containing fly-ash, the dosage rate may typically be twice the range quoted above).

Effects of Overdosing

The effect of overdosing MORTAIR®D is a function of the degree of overdose.

Overdosing with MORTAIR®D will result in a modest increase in air content and workability.

Dispensing

It is preferable that MORTAIR®D should be introduced into the mixer by automatic dispensing equipment. Equipment or advice on dispensing can be obtained from GCP Applied Technologies.

Health and Safety

For further information on Health and Safety matters regarding this product we recommend that you consult the relevant Safety Data Sheet from GCP Applied Technologies. In line with general chemical handling precautions avoid contact with skin or eyes and protective gloves/goggles should be worn.

Packaging

MORTAIR®D is supplied in both 15 or 205 non returnable drums and 1,000 litre totes. Alternatively, bulk deliveries can be arranged.

Storage

MORTAIR®D should be stored above 0 °C and protected from frost. If the product does freeze, it should be thawed out slowly and remixed mechanically prior to use.

Storage Life in Manufacturer 's Drums :

12 months from date of manufacture.

Storage Life in Bulk Storage:

12 months from date of delivery.

Technical Service

Our Technical Service department of GCP Applied Technologies is available to assist you in the correct use of our performance chemicals.

gcpat.uk | Customer Service: Tel: 01925 855330 Fax: 01925 855350

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

MORTAIR is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2020 GCP Applied Technologies Inc. All rights reserved.

GCP Applied Technologies (UK) Ltd, Gate St, Dukinfield SK16 4RU.

This document is only current as of the last updated date stated below and is valid only for use in the United Kingdom. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.uk. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2025-05-13

gcpat.uk/solutions/products/mortair-d