

SAFETRACK[®] INLAID ROAD REPAIR

Sealing System for the Reinstatement of Cracks, Joints and Slots

Product Description

SAFETRACK[®] INLAID ROAD REPAIR (SAFETRACK[®] IRR) is a HAPAS-Approved* liquid, cold-applied, fast-curing inlaid repair system for single and multiple cracks based on GCP Applied Technologies, previously Stirling Lloyd's, unique ESSELAC[®] advanced resin technology and extensive experience in the development of high performance reinstatement products.

SAFETRACK[®] IRR is available in both High Modulus (HM) and Flexible (F) grades as defined in the BBA Crack Sealing Guideline Document.

HM Grade – Suitable for static cracks and open seams in asphalt where no movement is expected.

F Grade – For use where movement is likely.

A major advantage of SAFETRACK[®] IRR is its fast cure and rapid return to service across the temperature range. To facilitate this both SAFETRACK[®] IRR "HM" and "F" grades are available in "Standard" and "Low Temperature (LT)" grades.

*Certificate No.10/H160, Product Sheet 3 & 7.

Uses

SAFETRACK[®] IRR has been developed for filling and sealing a recess in asphalt and concrete surfaces. The system is ideally suited for a range of applications, including:

- Inlaid crack, slot and joint repair, of any width
- Filling and supporting open or fretted joints in asphalt
- Repair of multiple cracks
- Remote traffic signal installation
- Re-instatement of Cross Carriageway Ducts (CCD's)
- Light Rail (Tram) seal, support and insulation
- Asphalt surface regulation prior to surfacing

Features

- First-time reinstatement
- Simple and economical to apply
- Rapid installation and cure ensure minimum downtime
- Cold-applied, no hot trades
- Long service life
- Resists deformation and rutting under traffic load
- Excellent retention of skid resistance
- Extends the life of asphalt
- Width of repair can be varied to suit application
- HAPAS Certified for minimum 5 year life

Technical Information

Application Temperature Range¹ 0 to 25 °C

TEMPERATURE ² / MATERIAL	TYPICAL WORKING LIFE	TYPICAL CURE TIME
SAFETRACK® IRR		
25 °C	5 minutes	10 minutes
20 °C	7 minutes	20 minutes
15 °C	10 minutes	35 minutes
10 °C	13 minutes	50 minutes
SAFETRACK® IRR LT		
15 °C	7 minutes	23 minutes
10 °C	10 minutes	30 minutes
5 °C	13 minutes	35 minutes
0 °C	15 minutes	40 minutes

Surface Preparation

The surface to be treated must be clean and dry. Use oil- and water-free compressed air to clear the crack or slot of all dirt, standing water and loose material.

Application

SAFETRACK® IRR consists of 2 components – a resin and BPO powder catalyst.

Before the final surface of the SAFETRACK® IRR is allowed to gel it is completely 'blinded' with dry aggregate to provide a skid-resistant finish.

Typical cure time is between 10 and 50 minutes, after which the road can be re-opened.

Full application training is provided by GCP and detailed Application Guidelines are available to the Authorised Contractor.

A range of simple hand tools and hand-propelled equipment is available from GCP to assist with application including:

- Draw boxes, 40mm to 200mm wide
- Trenchmaster, for slot filling
- Fillmaster, for high volume slot filling
- Fretmaster, for longitudinal joint repair
- Gripmaster, for dispersal of overscatter
- SAFETRACK[®] pumps, for use on larger projects for high outputs of material application

Coverage

SAFETRACK[®] Crack Infill 'HM' – 1.85kg/m²/mm

SAFETRACK[®] Crack Infill 'F' – 1.65kg/m²/mm Aggregate Overscatter is typically 4kg/m²

Coverage of resin will vary depending upon the size of the crack or slot and surface texture.

¹For temperatures outside this application range please contact GCP Technical Services.

²Based on ambient, material and substrate temperature all being the same

Maintenance & Repair

If a repair is required, fresh SAFETRACK[®] IRR is quickly and easily applied to the existing material, irrespective of the time since the previous installation, enabling the integrity and performance of the installed material to be maintained indefinitely.

Colour

The standard colour is Asphalt Grey. Also available in Neutral for concrete applications and as an indicator layer in asphalt.

Cleaning

All tools and equipment should be cleaned with Acetone before the material is allowed to cure.

Packaging & Storage

SAFETRACK[®] IRR 'HM': 25.25kg pack (inc. 250g of BPO)

SAFETRACK[®] IRR 'F': 25.6kg pack (inc. 600g of BPO)

Aggregate Overscatter – 25kg bag (sold separately to kit)

All components of the system should be stored in cool, dry, protected conditions, out of direct sunlight and in accordance with the relevant site Health & Safety regulations. Storage temperature must not exceed 25 °C. Do not store near naked flames or foodstuffs.

Stored in unopened containers, under the correct conditions, the components have a minimum shelf life of twelve months. If your product is more than twelve months old you must contact GCP before use.

Health & Safety

Please refer to our safety datasheets for further information.

General Information

SAFETRACK® IRR is part of a wide range of specialist highway maintenance, waterproofing, surfacing and repair materials manufactured and supplied by GCP. If you require any further information on this or any other of our products, please contact us or visit our website www.gcpat.com.



gcpat.com | Technical Services, Manchester, UK (+44 (0) 1565 633111)

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the end user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

ESSELAC® and SAFETRACK® are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved

MA809 SAFETRACK® INLAID ROAD REPAIR DATASHEET (Issue 3)

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP Applied Technologies (UK) Ltd, 487-488 Ipswich Road, Slough, SL1 4EP

This document is only current as of the last updated date stated below and is valid only for use in the United Kingdom. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.uk. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2023-02-02

gcpat.uk/solutions/products/safetrack-highway-maintenance-products/safetrack-inlaid-road-repair