

XT 5940

Cement Additive for Special Cements

Product Description

XT 5940 is a chemical additive to be interground during the manufacture of masonry cements and/or multipurpose cements, to provide good workability and long board life through controlled air entrainment and high water retention. XT 5940 eliminates the need to add at the job site separate materials to impart this combination of properties to the mortar. XT 5940 is based on an aqueous solution of selected raw materials to suit the requirements of the cement manufacture.

Physical Properties

XT 5940	
Appearance	Brown liquid
Density (g/l)	1050-1080
pH	8,5-10,5

Recommended Addition Rate

According to GCP experience the addition rate of XT 5940 is typically in the range of 600-1200 g/t of treated masonry cement. However the optimum addition rate of XT 5940 depends on the type of masonry cement and the performances requirements. GCP personnel are available for assistance. Deviation from the optimum cannot guarantee the expected results. Overdosing can increase the air entrainment.

Advantages

- Controlled air entrainment
- Excellent workability, extended boardlife
- Improved flexural bond strength
- High water retention
- Reduced tendency of re-agglomeration
- Improved flowability

Benefits

XT 5940 provides an air entrainment accomplished by the development of stabilised micro bubbles, which act like flexible ball bearings, increasing the plasticity and workability of the mortar produced with the treated cement. This technology, developed at the research laboratories of GCP, provides excellent workability and extended board life with a significantly lower amount of air than the more traditional technologies, so that other mechanical properties, as the flexural bond strength, are improved.

Through the higher water retention, placeability is improved and bleeding, plastic shrinkage and segregation are minimised.

XT 5940 is also a grinding aid which reduces the tendency of reagglomeration of the fine particles formed during the comminution process.

XT 5940 permits improvements of the flowability, of the efficiency of mill and separator and thus increase in production rate with corresponding reduction in grinding energy.

XT 5940 controls effectively the setting process and permits significant extension of the board life.

XT 5940 enhances the hydration process of the hydraulic binder and therefore mortars with higher compressive strengths can be produced.



Certification

XT 5940 meets the requirements of EN 197.

Typical Applications

XT 5940 is designed for the economical production of high quality masonry cement such as Type MC 5 and MC 12.5 described under ENV 413. Multipurpose cements with high filler contents can also be produced in compliance with the EN 197 requirements.

How to Use

XT 5940 should be added on to the feed belt or injected pure or diluted (also with the cooling water) into the mill. For an accurate proportioning of XT 5940 a volumetric metering pump is suitable. GCP personnel are available for assistance.

Packaging and Storage

XT 5940 is supplied in 205 litre drums, in 1000 litre plastic containers or bulk.

XT 5940 does not require particular precaution for the storage. Care has to be taken during the unloading operation: it would be suggested to fill the tank from the bottom.

XT 5940 has to be protected from freezing.

For tanks and containers placed outside a heating system or a re-mixing device is suitable.

It is also better to insulate exposed pipelines.

GCP personnel can help in designing the best system.

Shelf life is at least 12 months if stored in sealed manufacturer's containers.

Handling Precautions

XT 5940 does not require particular precaution for health and safety. For further advice please read the Material Safety Data Sheet. Accidental release or spillage to be absorbed with an inert, non combustible material, such as sand or sawdust. Tanks and container can be cleaned with water.

REACH

All of our products sold in the EU comply with REACH obligations. Our customers, as manufacturers or downstream users may sell their products utilizing GCP Applied Technologies products with confidence that the substances in them may be placed on the market in compliance with REACH.

gcpat.uk | Manufacturing and Technical Service Contacts: Tel: +44 (0)1925 855330

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

Copyright © 2018 GCP Applied Technologies Inc. All rights reserved.

GCP0082_XT-5940_GB_Widnes_1220 sm

This document is only current as of the last updated date stated below and is valid only for use in the United Kingdom. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.uk. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2025-05-13

gcpat.uk/solutions/products/xt-5940